

PRODUCT INFORMATION

IONAC® NM-60



Ionac® NM-60 is a highly regenerated mixed bed ion exchange resin consisting of a 1:1 chemically equivalent mixture of a type 1, strong base anion exchange resin and a strong acid cation exchange resin. **Ionac® NM-60** is specially treated for high conversion and low TOC to meet the most exacting standards of high purity water industry.

The resin mixture is ready for the use without regeneration. **Ionac® NM-60** is especially suitable:

- » in mixed bed units for polishing after primary demineralization systems
- » in process industries
- » in electronic industries
- » in small industrial plants (e.g. refilling of starter batteries or coolant circuits)
- » for rad waste application
- » in demineralization systems

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Ion Exchange Resins.

This document contains important information and must be read in its entirety.

Edition: 2010-11-11
Previous Edition: 2010-08-27

LANXESS
LANXESS Sybron

General Description

Ionic form as shipped	H ⁺ /OH ⁻
Functional group	sulfonic acid/quat. amine type I
Matrix	crosslinked polystyrene
Structure	gel type beads
Appearance	dark brown - black, translucent

Physical and Chemical Properties

		metric units	
Operating capacity*	breakthrough point 1 megohm*cm	min. eq/l	0.40
Fines*	< 0.315 mm	max. vol. %	2
Coarse beads*	> 1.25 mm	max. vol. %	5
Bulk density	(+/- 5 %)	g/l	688
Density		approx. g/ml	1.1
Water retention		wt. %	50 - 60
Volume change	H ⁺ /OH ⁻ -->Ca, Mg/Cl, SO ₄	max. vol. %	- 20
Stability	at pH-range		0 - 14
Storability	of the product	max. years	2
Storability	temperature range	°C	4 - 24

* Specification values subjected to continuous monitoring.

Recommended Operating Conditions*

	metric units	
Operating temperature	max. °C	60
Operating pH-range		0 - 14
Bed depth	min. mm	600
Specific pressure drop (15 °C)	approx. kPa*h/m ²	1.5
Pressure drop	max. kPa	200
Linear velocity operation	max. m/h	60

* The recommended operating conditions refer to the use of the product under normal operating conditions. It is based on tests in pilot plants and data obtained from industrial applications. However, additional data are needed to calculate the resin volumes required for ion exchange units. These data are to be found in our Technical Information Sheets.

Additional Information & Regulations

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

Toxicity

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

Disposal

In the European Community Ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Lanxess Deutschland GmbH
BU ION
D-51369 Leverkusen

lewatit@lanxess.com

www.lewatit.com
www.lanxess.com

This document contains important information and must be read in its entirety.

Edition: 2010-11-11
Previous Edition: 2010-08-27